



MELTEX Co Ltd.

Product Data Sheet

Product Code: MTLAMP3D

Product Description: 100% Micro semi dull Polyester twill face fabric laminated with a PFTE film to a 30g polyester knit 3 Layer Bivi Bage

TEST	SPECIFICATION	TEST METHOD
Base Fabric	75f72x75f72 Semi dull	
Construction	Poly micro twill	
lamination	PU	ISO 11092
Finish	WR	
Fabric Weight	N/A	AS 2001.2.13.1987
Coated Weight	N/A	
Total Weight	185g/m2	AS 2001.2.13.1987
Useable Width	140cm	AS 2001.2.12.1987
Thickness	<0.4 mm	AS 2001.2.15.1989
Tensile Strength Warp (N)	950N	AS 2001.2.3.1.2001
Tensile Strength Weft (N)	1000N	AS 2001.2.3.1.2001
Tear Strength Warp (N)	25N	AS 2001.2.10.1986
Tear Strength Weft (N)	35N	AS 2001.2.10.1986
Flex Crackin	100000 cycles	AS 4878.9.2001
Delamination	100000 cycles	AS 4978.9.2001
Colour Fastness to Light	5	AS 2001.4.B02.2001
Colour Fastness to Water	4	AS 2001.4.E01.2001
Colour Fastness perspiration acid	4	AS 2001.4.E04.2005
Colour Fastness perspiration alkaline	4	AS 2001.4.E04.2005
Colour Fastness dry cleaning perchloroethylene	4	AS 2001.4.16.1981
Colour Fastness dry cleaning white spirt	4	AS 2001.4.16.1981
Colour Fastness to Washing 40c Test K3	4	AS 2001.4.E02.2001
Colour Fastness to Sea Water	4	AS 2001.4.E02.2001
Fastness to Rubbing Wet Dry	4	AS 2001.4.3.1995
Dimensional Stability	2%	AS 2001.5.4.2005
Water Repellency	5	AS 2001.2.16.1987
Water Repellency after 5 wash/5 dry	4	AS 2001.2.16.1987

Product Code:MTLAMP3D

Water Resistance	8000mmISO 20811	
Water Resistance after wash	8000mISO 20811	
Air Permeability	0	AS 2001.2.34
PH Value	6/7	AS 2001.3.1.1998
Breathability	Ret less than 7	ISO 11092.1983
Blocking	0	AS 4878.11.2001

WASHING INSTRUCTION



- 1.Cool machine wash 40C
- 2.No Bleach or colour additives
- 3.Tumble dry gentle cycle low heat
- 4.Cool Iron no steam

ADDRESS: TEXCHANNEL IMP. & EXP. CO., LTD.
Room 605 Fortune Center No 100 Lujiang Road Xiamen 361001 China

SIGNED:



DISCLAIMER: The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.